

Aniline oiled pull up leather which is distinctive by the fact that the selected hides have some natural markings to add character and uniqueness to the finished furniture. (Hide size av. 4.5sqm, thickness ca. 1.0mm)

|   |  |
|---|--|
| <b>Applications</b>                             | Suitable for residential, contract.  |
| <b>Natural Leather</b>                          | Leather is a natural product and the uniqueness of each hide is identified on occasion by growth marks, scars, variations in grain and other natural characteristics which add to the beauty of real leather and should not be regarded as a defect. Due to the natural properties of leather, colour and texture variations between batches may occur.  |
| <b>Care Information</b>                         | <ul style="list-style-type: none"> <li>✓ Extra care is required as aniline leather is more susceptible to marking, soiling and spillage marks.</li> <li>✓ Wipe away stains with a soft damp cloth as soon as they occur.</li> <li>✓ Dust with a soft cloth and Vacuum frequently.</li> <li>✓ Futura cleaners and conditioners are available to help maintain this leather type and will be beneficial if used from new.</li> </ul> |
| <b>Precautions<br/>Protect from /<br/>Avoid</b> | <ul style="list-style-type: none"> <li>✗ Sources of excessive heat, i.e. fires or close to radiators</li> <li>✗ Direct sunlight particularly on aniline and semi aniline types</li> <li>✗ Furniture polishes and waxes</li> <li>✗ Household detergents and solvents</li> </ul>   |
| <b>Characteristics<br/>and Test<br/>Methods</b> | Manufactured under the ISO9001:2008 quality system and to comply with British / European standards for upholstery leather and the furnishings fire safety regulations 1988.  |

| Characteristic                               | Method                                | Recommended Values     |
|--|---------------------------------------|------------------------|
| Fastness to Rubbing 50 dry                   | EN ISO 11640<br>EN ISO 11641          | min 3 grey scale       |
| Fastness to Rubbing 20 wet                   |                                       | min 3 grey scale       |
| Fastness to Rubbing 20 alkaline ph8          |                                       | min 3 grey scale       |
| Flexing Endurance                            | N/A                                   | N/A                    |
| Tear Strength                                | EN ISO 3377-1                         | ≥ 20 N                 |
| Surface Adhesion                             | N/A                                   | N/A                    |
| Colour Fastness to Light                     | EN ISO 105-B02                        | Min 3 blue scale       |
| Fire Resistance - Domestic                   | BS5852:part 1 ign. source 0 cigarette | Pass                   |
| Fire Resistance - Domestic                   | BS5852:part 1 ign. source 1 match     | Pass                   |
| FR – Contract (specify requirement on order) | BS5852 Crib/Source 5                  | Pass (after treatment) |

All our leathers comply with strict regulations and EU directives covering the use and presence of PCP, CFC, ChromoVI, Dimethylfumarate (DMF) and Azo dyestuffs during the tanning process.